

Technical Bulletin

TSC Solder Paint

Alloys: Leaded / Pure Tin

DESCRIPTION

TSC Solder Paint is a uniform mixture of finely powdered solder and zinc chloride activated flux, having a creamy consistency, for pre-tinning and solder coating. It has been especially formulated to keep the heavy solder powder in suspension and to reduce the settlement of the metal powder and therefore making it easier to restir and an aid to prolong its shelf life.

If the metal powder does settle to the bottom of the container, then this is easily reconstituted with light stirring.

BENEFITS

- High activity flux
- Improved shelf life
- Ease of application
- Paint easily restirred

APPLICATION METHODS

For tinning the article is brushed or sprayed with the Solder Paint and heated until the solder melts to form an adherent coating. For soldering, the joint members should be coated before assembly, thus correctly locating the solder in the joint. To complete the joint, heat is applied until sweating occurs.

The solder paint should be applied to the metal surfaces to be tinned or sweat soldered in the cold state. As with other zinc chloride based fluxes, the residues can be corrosive and in most applications it is appropriate to wash the tinned area to remove these residues.

TECHNICAL SPECIFICATION

Metal loading is 70% by weight. A choice of five alloy grades are available.


| Grade | Melting or Solidus / Liquidus Temp °C | Uses |
|-----------------------|---------------------------------------|---|
| S-Sn40Pb60 | 183 - 235 | All general sweating and tinning work |
| S-Sn97Cu3 Pure Tin | 230 - 250 232 | Hand tinning Sweat soldering where a lead free solder is essential |

MATERIAL CHARACTERISTICS

| Characteristic | Data |
|----------------------|----------------------|
| Appearance | Grey, slurry, creamy |
| Odour | Faint |
| Density @ 20C (g/ml) | 4 |
| PH | Acidic |

PACKAGING

TSC Solder Paint is available in various container sizes: 125g, 500g and 2.5Kg .



SOLDER CONNECTION

Email: sales@solderconnection.co.uk | Tel: +44(0)1291 624 400

TSC Solder Paint

Alloys: S-Sn25Pb75 / S-Sn40Pb60 / S-Sn60Pb40 / S-Sn97Cu3 / Pure Tin

TECHNICAL SUPPORT

Please refer to your local Sales Office.

HEALTH AND SAFETY

Materials containing Lead are subject to the Control of Lead at Work Regulation. Eye and skin protection must be used when handling or working with fluxes. Always wear safety goggles and suitable rubber gloves. Avoid breathing fumes evolved during soldering process by providing fume extraction or good ventilation. In case of contact, immediately flush eyes or skin with plenty of water for at least 15 minutes. Obtain medical attention.

Refer to Health and Safety Data Sheet for more detailed information.

STORAGE

Room temperature storage only. No refrigeration necessary.
Do not allow to Freeze

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of the materials designated.