

Technical Bulletin

Issue 1 - 14/09/22

TSC Leaded Flux Cored Electrical Solder Wire

DESCRIPTION

TSC Leaded Flux Cored Electrical Solder Wires are ideal for general hand soldering operations. TSC Electrical Solder Wire will work well for all electrical wiring applications, together with some more mechanical assembly work, typically when soldering to clean copper and brass sheet details such as found in most of the engineering models today.

Following soldering, post solder flux residues around the joint will be fairly light and can be safely left on any electrical connection, due to excellent insulative properties of the flux. If removal is required for cosmetic appearances, a range of materials both solvent and aqueous based. Please feel free to contact our technical department where one of the team would be pleased to offer advice regarding a suitable product to suit your application.

This wire is supplied on 50g reels as standard but may be available in larger quantities on request.

FEATURES AND BENEFITS

- Very fast wetting → Low Cycle times for component touch-up and manual assembly
- Good spread characteristics → Excellent Solder Joints
- Pleasant pine smell → Operator Friendly
- Clear and safe residue → No-Clean Residues, Useful for all Applications
- Provides good joint appearance → Makes Inspection easy
- ROL1 per IPC J-STD-004-A

PRODUCT INFORMATION

Alloy	Melting or Solidus / Liquidus Temp °C	Flux
Sn60/Pb40	183 - 190	2.2%

APPLICATION

It is important to match the geometry of the solder tip to the size of lead or component pad you are working on. As a guide line for lead free solders a tip temperature of between 370° - 425°C is ideally suited. For leaded alloys a temperature of 300° - 400°C is recommended.

HANDLING & STORAGE

All cored solder wires should be stored in clean dry areas away from moisture and direct sunlight. Do not freeze.


Shelf life:

3 years

< 40°C

CLEANING

TSC Leaded Flux Cored Electrical Solder Wire is a no clean solder wire and therefore residues do not need to be removed. If cleaning is required or for advice on your application contact one of our Sales Offices.



SOLDER CONNECTION

UK: +44(0)1291 624 400

solderconnection.com

Ire: +353 (1) 842 1172

TECHNICAL DATA

	Specifications
Rosin Grade	WW per Fed Spec. LL-R-626
Rosin Softening Point	71°C (160°F)
Acid Value	170 - 190 mg KOH/g flux (IPC-TM-650-2.3.13)
Halide Content	0.35 - 0.45% weight (IPC-TM-650-2.3.28.1)
Copper Mirror	<50% breakthrough per IPC J-STD-004A
Classification	ROL1
SIR	PASS

SAFETY

Observe standard precautions for handling and using the solder wire. TSC Leaded Flux Cored Electrical Solder Wire is not considered toxic, however soldering will produce fumes during operation therefore it would be good practice to adequately exhaust / vent the fumes away from the operator.

Solder Connection supplies a full range of LEV (local exhaust ventilation) equipment available that may be suitable for your application. Contact our local office to discuss your requirements.

Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of the materials designated.