

Technical Bulletin

TSC NR-205 Rework Flux

DESCRIPTION

TSC NR-205 Rework Flux is a halide-free, rosin / resin free, low solids, no-clean flux. Particularly well suited to touch up / rework applications can be supplied in a sealed flux applicator pen or in one litre containers for refilling reusable dispensers. The flux produces a tack-free surface with high surface insulation resistance and very little residue to interfere with electrical testing.

TSC NR-205 fully conforms to the stringent requirements of Bellcore Spec. TRNWT-000078. The flux has been specifically formulated to resist degradation in surface insulation resistance and electro-migration, even in situations where the flux does not fully experience soldering temperatures and when heavy levels of flux may have been accidentally applied. The residues are non-corrosive and will not cause "greening" when in contact with copper or copper-bearing alloys.

TSC NR-205 Flux is particularly well-suited for touch-up / rework when supplied as a sealed flux pen giving precise control in difficult or hard to access areas.

FEATURES & BENEFITS

- Designed specifically for touch-up / rework applications.
- Excellent solderability.
- Meets Bellcore requirements & other critical SIR tests.
- Non-corrosive residues.
- High Reliability, even when the flux does not experience soldering temperatures
- Will not cause "greening" on exposed copper/copper alloys,
- Supplied in either flux applicator pens or 1 litre containers.

APPLICATION

For application via the flux pen, the nib should be lightly wiped on and around the solder joint to be reworked. Once a suitable amount of flux has been applied the manual soldering operation can be performed..

AVAILABILITY

TSC NR-205 flux is available in Pen format, alongside 125ML, 250ML, 1L, 5L and 10L containers.

TECHNICAL DATA

Flux Classification	Specifications
Appearance	ORLO
Solids Content (wt/wt)	Clear, Colourless Liquid
Specific Gravity @ 25°C (77°F)	2.15
Acid Number (mg KOH/g)	0.797 ± 0.002
Copper Mirror	16.5 ± 1.0
Corrosion	Pass
Halides	Pass
Bellcore SIR	Pass
Flash Point (T.C.C.)	Pass
	13°C (56°F)

solderconnection.com

Unit 5 | Severn Link Distribution Centre
Chepstow | Monmouthshire | NP16 6UN

CORROSION / ELECTRICAL TESTING

CORROSION TESTING

Test	Requirement	Results
IPC/Bellcore Copper Mirror Test	No complete removal of copper	Passes
Halide-silver chromate paper method	No detection of halide	Passes
IPC-SF-818 10-day Copper Corrosion Test	No evidence of corrosion	Passes as Type "L"

SURFACE INSULATION RESISTANCE (All Values in Ohms)

Method	Conditions	Requirement	Result
IPC-SF-818,	85°C/85% RH	1.0x10 ⁸ min.	5.6x10 ⁹
Class 3, Not Cleaned	7 Days		

BELLCORE-TR-NWT-000078, Issue 3

Comb Pattern "Up" (uncleaned)	35°C/85% RH (4 days with bias voltage)	1.0 X 10 ¹¹ min.	1.3 X 10 ¹²
Comb Pattern "Down" (uncleaned)	35°C/85% RH (4 days with bias voltage)	1.0 X 10 ¹¹ min.	1.9 X 10 ¹²
Control Boards	35°C/85% RH (4 days with bias voltage)	2.0 X 10 ¹¹ min.	3.3 X 10 ¹²

ELECTROMIGRATION (Per Bellcore TR-NWT-000078, Issue 3, All Values in ohms)

Method	Conditions	SIR (Init.)*	SIR (Final)*	Visual
Comb Pattern "Up"	85°C/85% RH 500 Hrs. / 10 V. bias	1.2 X 10 ⁹	5.0 X 10 ⁹	No dendrites or corrosion
Comb Pattern "Down"	85°C/85% RH 500 Hrs. / 10 V bias	5.4 X 10 ⁹	3.4 X 10 ⁹	No dendrites or corrosion

* For passing electromigration, SIR (Init.) / SIR (Final) <10

HANDLING & STORAGE

Store in a closed container at room temperature. Solder flux shelf life is 36 months years from date of manufacture.

HEALTH & SAFETY

TSC NR-205 contains hazardous ingredients, therefore, the flux should be disposed of in accordance with all local, regional, national and international regulations. Flammable, keep away from sparks and open flames. Empty containers can still be a flammable hazard from residual vapours. Remove skin splashes by immediate washing with soap and water.

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of the materials designated.

solderconnection.com

Unit 5 | Severn Link Distribution Centre
Chepstow | Monmouthshire | NP16 6UN

sales@solderconnection.co.uk
Office: 01291 624 400