

Technical Bulletin

Solder Connection Dry Workshop Wipes

PRODUCT SPECIFICATIONS

Composition (%)	Hydro-entangled, Polyester 45, Cellulose 55
Binder	None
Optical brightener	None
Weight (g/ m ²) <i>ISO 9073-1</i>	65.93 – 72.87
Thickness (mm) <i>ISO 9073-2</i>	0.285 – 0.315
Liquid Absorptive Capacity (%) <i>ISO 9073-6</i>	366.60 – 448.07
Liquid Absorbency Time (s) <i>ISO 9073-6</i>	2.23 – 2.73
<u>Tensile strength (N/ 50mm)</u>	
MD dry	199.3
CD dry	55.4
MD wet	144.8
CD wet	41.10
<u>Elongation (%)</u>	
MD dry	23.0
CD dry	87.0
MD wet	26.0
CD wet	68.5
Elmendorf tearing resistance CD (mN)	5933



Particles >0.5 µm/ m ² (x10 ⁶) <i>IEST-RP-CC004.3</i>	≤ 878
Fibres > 100 µm/ m ² (x10 ⁶) <i>IEST-RP-CC004.3</i>	≤ 1.05
<u>Non-volatile Residues (g/ m²) <i>IEST-RP-CC004.3</i></u>	
DI Water	≤ 0.063
Isopropyl Alcohol	≤ 0.017
<u>Metals and ions (µg/ g or ppm) <i>IEST-RP-CC004.3</i></u>	
Ca ²⁺	≤ 27.8
Mg ²⁺	≤ 16.0
K ⁺	≤ 9.58
Na ⁺	≤ 65.9



The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of the materials designated.